

RTP 1401 L

PESU-GF10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	4826	MPa	ASTM D 638
Tensile Strength	96.5	MPa	ASTM D 638
Flexural Modulus	4482	MPa	ASTM D 790
Flexural Strength	152	MPa	ASTM D 790
Rockwell Hardness	R 121	-	ASTM D 785
Izod Impact notched, 1/8 in	37.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.508	mm	-
DTUL @ 66 psi	207	°C	ASTM D 648
DTUL @ 264 psi	204	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	15	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.007	-	ASTM D 150
Dielectric Constant, 1 MHz	3.7	-	ASTM D 150
Other properties			
Water Absorption, 24hr	0.4	%	ASTM D 570
Density	1440	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	343 - 377	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific