

**Product Texts**

LNP THERMOCOMP JF006EXZ compound is based on Polyethersulfone (PES) resin containing 30% glass fiber. Added features of this grade include: Easy Molding.

UL Yellow Card Link [E121562-101283894](https://www.ul.com/yellow-card/E121562-101283894)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.4	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.7	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break	145	MPa	ISO 527
Strain at break	1.9	%	ISO 527
Flexural modulus	9700	MPa	ISO 178
Flexural strength	209	MPa	ISO 178
Izod impact strength, +23°C, 4mm	40	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Strength at Break	139	MPa	ASTM D 638
Elongation at Break	2.6	%	ASTM D 638
Flexural Modulus	8910	MPa	ASTM D 790
Flexural Strength	192	MPa	ASTM D 790
Izod Impact notched, 1/8 in	77	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	550	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	213	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.5	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	212	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.21	%	ASTM D 570
Density	1600	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	355 - 370	°C	-
Mold temperature	140 - 150	°C	-
Zone 1	345 - 355	°C	-
Zone 2	360 - 370	°C	-
Zone 3	370 - 380	°C	-
Screw speed	60 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific