

## Product Texts

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

**Rynite® 935 NC010 is a 35% mica/glass reinforced modified polyethylene terephthalate resin with low warpage and excellent electrical properties.**

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1320	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.32	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	1790	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	1.4E-7	m <sup>2</sup> /s	-
<sup>[C]</sup> Ejection temperature	170	°C	-
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.0028	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0052	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10200	MPa	ISO 527
<sup>[C]</sup> Stress at break	85	MPa	ISO 527
<sup>[C]</sup> Strain at break	2	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	9350	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	7690	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	20	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	4	kJ/m <sup>2</sup>	ISO 179/1eA
<b>ASTM Data</b>			
Tensile Modulus	9930	MPa	ASTM D 638
Tensile Strength	89.6	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Compressive Strength	141	MPa	ASTM D 695
Flexural Modulus	9600	MPa	ASTM D 790
Flexural Strength	141	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785
Izod Impact notched, 1/8 in	64	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	43	J/m	ASTM D 256
Temperature	-40	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	252	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	235	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	205	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	16	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	52	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

**Rynite® 935 NC010**

PET-(P+GF)35

Celanese

Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<sup>[C]</sup> Oxygen index	<b>21</b>	%	ISO 4589-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>16</b>	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	<b>52</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>241</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>215</b>	°C	ASTM D 648
Melting Temperature	<b>252</b>	°C	ASTM D 3418

<sup>[C]</sup>: CAMPUS

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>4.5</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>4.1</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>300</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>140</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>1E14</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>39</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>300</b>	-	IEC 60112
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>23.5</b>	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	<b>0.01</b>	-	ASTM D 150
Dielectric Constant, 1 MHz	<b>3.7</b>	-	ASTM D 150
Surface Resistivity	<b>1E14</b>	Ohm	ASTM D 257
Volume Resistivity	<b>1E15</b>	Ohm*cm	ASTM D 257

<sup>[C]</sup>: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>0.83</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.13</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1580</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1580</b>	kg/m <sup>3</sup>	ASTM D 792

<sup>[C]</sup>: CAMPUS**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Additives**

Release agent

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Low Warpage, Weldable

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa