

**ASPET AS 21CF**

PET

Dhunseri Ventures Limited

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>248</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Intrinsic Viscosity	<b>0.84</b>	dl/g	-
Acetaldehyde	<b>1</b>	ppm	-
Color L	<b>83.5</b>	-	CIE
Color b	<b>-1.5</b>	-	CIE
Crystallinity	<b>50</b>	%	-
Moisture Content	<b>0.25</b>	%	-

**Characteristics****Processing**

Blow Molding

**Applications**

General Purpose, Packaging

**Features**

Barrier Properties, Copolymer

**Regional Availability**

Asia Pacific

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR