

BAPOLENE® 83

PET

Bamberger Polymers, Inc.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	252	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ASTM D 792
Intrinsic Viscosity	0.83	dl/g	-
Acetaldehyde	2	ppm	-
Crystallinity	50	%	-
Moisture Content	0.1	%	-

Characteristics**Processing**

Injection Molding, Blow Molding

Certifications

Food contact, Food approval FDA 21 CFR

Features

Copolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa