

Bondz BO 075

PET

Selenis Portugal, S.A.

Thermal properties	Value	Unit	Test Standard
Other Standards^{S1}			
Glass Transition Temperature	74	°C	ASTM D 3418

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.68	dl/g	-
Color L	63	-	CIE
Color b	1	-	CIE
Moisture Content	0.3	%	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Type of extrusion	film	-	-
Pre-drying - Temperature	60 - 65	°C	-
Pre-drying - Time	8	h	-
Processing humidity	≤0.004	%	-
Melt temperature	250 - 270	°C	-

Characteristics**Processing**

Film Extrusion

Certifications

Food contact

Delivery form

Pellets

Regional Availability

North America, Europe, South and Central America

Features

Amorphous, Good Adhesion, Heat Sealable, Low Odor, Melt Strength, Copolymer