

Calima CA 360

PET

Selenis Portugal, S.A.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	253	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Acetaldehyde	1	ppm	-
Color L	85	-	CIE
Color b	1	-	CIE
Crystallinity	50	%	-
Moisture Content	0.2	%	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	175	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.004	%	-
Melt temperature	285 - 295	°C	-

Characteristics**Delivery form**

Pellets, White

Special Characteristics

Opaque

Features

Low Odor, Copolymer

Certifications

Food contact, Food approval 10/2011

Regional Availability

North America, Europe, South and Central America