

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2344	MPa	ASTM D 638
Tensile Strength at Yield	56	MPa	ASTM D 638
Flexural Modulus	2275	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	61.1	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1330	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Certifications

Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved

#### Applications

Automotive, Medical

#### Regional Availability

North America