

Eköpet 80

PET

JSC Ekopet

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	246	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.8	dl/g	-
Acetaldehyde	1	ppm	-
Color L	82	-	CIE
Color b	1	-	CIE
Moisture Content	0.2	%	-

Characteristics

Delivery form

Pellets

Features

Copolymer

Chemical Resistance

Oil Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

Europe