

FuTuRe PET 1125

PET

Indorama Ventures PCL

Thermal properties	Value	Unit	Test Standard
Other Standards^[5]			
Melting temperature, 10°C/min	240	°C	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.84	dl/g	-
Acetaldehyde	0.5	ppm	-
Color b	-2.5	-	CIE
Crystallinity	53	%	-
Moisture Content	0.15	%	-
Bulk density	900	kg/m ³	-
Other Standards^[5]			
Density	1400	kg/m ³	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Blow Molding

Special Characteristics

Transparent

Features

Barrier Properties, High Gloss, Copolymer

Chemical Resistance

Oil Resistance

Certifications

Recycled Resin Content, Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, South and Central America