

Krupet-A Pellets blue

PET

Steinbeis PolyVert GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	40	g/10min	ISO 1133
Temperature	280	°C	-
Load	2.16	kg	-
Other properties			
Density	1370	kg/m ³	ISO 1183
Intrinsic Viscosity	0.76	dl/g	-
Acetaldehyde	5	ppm	-
Color L	56	-	CIE
Color a	0.5	-	CIE
Color b	13	-	CIE
Moisture Content	0.2	%	-
Bulk density	860	kg/m ³	-

Characteristics

Delivery form

Pellets

Regional Availability

Europe

Certifications

Recycled Resin Content