

Product Texts

Property	Value	Unit
Fine Particles Content	500 max.	ppm
Weight of 100 Granules	1.5	g

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	247	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	78	°C	ISO 11357-1/-2

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.84	dl/g	-
Acetaldehyde	1	ppm	-
Color b	2.5	-	CIE
Crystallinity	50	%	-
Moisture Content	0.4	%	-
Bulk density	880	kg/m ³	-

Characteristics**Processing**

Injection Molding, Blow Molding

Applications

Packaging

Features

Copolymer

Regional Availability

Europe

Certifications

Recycled Resin Content, Food contact