

Product Texts

SKYGREEN® S2008 is a glycol-modified polyethylene terephthalate (PETG) with excellent clarity and processability that makes it an attractive solution for versatile end-use applications.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	49	MPa	ISO 527
Yield strain	4.1	%	ISO 527
Stress at break	30	MPa	ISO 527
Strain at break	240	%	ISO 527
Flexural modulus, 23°C	1920	MPa	ISO 178
Flexural strength	67	MPa	ISO 178
Izod notched impact strength, +23°C	8.8	kJ/m ²	ISO 180/1A
Rockwell hardness	R 110	-	ISO 2039-2

ASTM Data			
Tensile Strength at Yield	44.6	MPa	ASTM D 638
Tensile Strength at Break	40.2	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Flexural Modulus	2109	MPa	ASTM D 790
Flexural Strength	69.2	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	64	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	73	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	70	°C	ASTM D 648
DTUL @ 264 psi	62	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	90	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Sheet Extrusion

Special Characteristics

Transparent, Sterilizable

Certifications

Food contact, Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved

Applications

Medical, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America