Volaprint PETG

PETG — Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**3000**	MPa	ISO 527
Charpy notched impact strength, +23°C	**5**	kJ/m²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	**1270**	kg/m³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Delivery form

Monofilament

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.