

BESTDUR PHG3

PET-GF15

Grupo Triesa

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	78	MPa	ISO 527
Strain at break	5	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	250	-	IEC 60112
Other properties			
Water absorption	0.5	%	Sim. to ISO 62
Density	1390	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Delivery form

Pellets, Natural Color

Regional Availability

Europe