

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	7000	MPa	ISO 527
Stress at break	105	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod impact strength, +23°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	6 -30	kJ/m <sup>2</sup> °C	ISO 180/1A -
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	250	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	180	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	225	°C	ISO 75-1/-2
Vicat softening temperature, B	215	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	HB 0.8	class mm	IEC 60695-11-10 -
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	225	-	IEC 60112
<b>Other properties</b>			
Density	1450	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.08	%	-

## Characteristics

### Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

### Regional Availability

Europe