

PRECITE® E GF 20 natural (7301)

PET-GF20

Akro-Plastic GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	7800	MPa	ISO 527
Stress at break	145	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	8500	MPa	ISO 178
Flexural strength	225	MPa	ISO 178
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
Density	1470	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Applications

Automotive, Electrical and Electronical

Chemical Resistance

General Chemical Resistance

Regional Availability

Europe, Asia Pacific