

**Tarolox 111 G4 DX02**

PET-GF20

Taro Plast S.p.A.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>9000</b>	MPa	ISO 527
Strain at break	<b>2.8</b>	%	ISO 527
Flexural modulus, 23°C	<b>8200</b>	MPa	ISO 178
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>50</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>256</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>236</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>240</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
Limiting Oxygen Index	<b>32</b>	%	ASTM D 2863

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Comparative tracking index	<b>225</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>0.06</b>	%	Sim. to ISO 62
Density	<b>1630</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Pellets

**Features**

Low Odor

**Additives**

Release agent

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Regional Availability**

Europe