

ISOBLEND® A65

(PC+ABS)

Sirmax S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	50	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	35	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	35	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, B	118	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	260	°C	-
Mold temperature	70	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Certifications

RoHS compliant

Applications

Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America