

HEG3630

PET-GF30

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	265	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Strength	130	MPa	ISO 527
Flexural modulus, 23°C	8500	MPa	ISO 178
Flexural strength	200	MPa	ISO 178
Charpy notched impact strength, +23°C	7.5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength	150	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	11000	MPa	ASTM D 790
Flexural Strength	250	MPa	ASTM D 790
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	225	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	253	°C	ASTM D 648
DTUL @ 264 psi	230	°C	ASTM D 648
Electrical properties			
ISO Data			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Other properties			
Density	1580	kg/m ³	ISO 1183
Density	1600	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	245 - 275	°C	-
Mold temperature	100 - 120	°C	-
Zone 1	245 - 260	°C	-
Zone 2	250 - 265	°C	-
Zone 3	255 - 270	°C	-
Nozzle temperature	260 - 275	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.2 - 0.8	MPa	-

Characteristics

HEG3630

PET-GF30

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Fatigue Resistance

Applications

Automotive, Electrical and Electronical

Regional Availability

Asia Pacific