

KOPET® KP132G30V0BL

PET-GF30

Kolon Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	118	MPa	ASTM D 638
Flexural Modulus	8630	MPa	ASTM D 790
Flexural Strength	177	MPa	ASTM D 790
Izod Impact notched, 1/8 in	54	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	245	°C	ASTM D 648
DTUL @ 264 psi	220	°C	ASTM D 648
Melting Temperature	255	°C	ASTM D 3418
Other properties			
Density	1660	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Black

Regional Availability

North America, Asia Pacific

Special Characteristics

Flame retardant