

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>126</b>	MPa	ISO 527
Strain at break	<b>1.7</b>	%	ISO 527
Flexural modulus, 23°C	<b>9200</b>	MPa	ISO 178
Flexural strength	<b>215</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>7.3</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>228</b>	°C	ISO 75-1/-2
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Yellow Card available	<b>yes</b>	-	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>7E14</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>18</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>200</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1650</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Delivery form**

Black

**Special Characteristics**

Flame retardant

**Additives**

Flame retarding agent

**Regional Availability**

Asia Pacific