

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13000	MPa	ISO 527
Stress at break	140	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Izod impact strength, +23°C	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	7 -30	kJ/m ² °C	ISO 180/1A -

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-0 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	V-0 0.8	class mm	IEC 60695-11-10 -

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	200	-	IEC 60112

Other properties	Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1710	kg/m ³	ISO 1183
Moisture Content	0.08	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	4	h	-
Melt temperature	260 - 280	°C	-
Mold temperature	120 - 140	°C	-
Feed temperature	50 - 70	°C	-
Holding pressure	60 - 100	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Delivery form

Natural Color

Regional Availability

Europe