

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Melt flow index, MFI	1.5	g/10min	GOST 11645-73

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Yield stress	9.3	MPa	GOST 11262-2017
Stress at break	11.8	MPa	GOST 11262-2017
Strain at break	600	%	GOST 11262-2017

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Density	919	kg/m <sup>3</sup>	GOST 15139-69

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Processing

Film Extrusion

### Delivery form

Pellets

### Certifications

Food contact

### Applications

Medical, Packaging, Toys

### Regional Availability

Europe, Asia Pacific