

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	3.5	g/10min	GOST 11645-73

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^[5]			
Density	919	kg/m ³	GOST 15139-69

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Film Extrusion

Applications

Medical, Packaging, Toys

Delivery form

Pellets

Regional Availability

Europe, Asia Pacific

Certifications

Food contact