

Product Texts

100% PCR Content

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.02	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.2	MPa	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	85	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	945	kg/m ³	ASTM D 792

Characteristics

Delivery form

Natural Color

Certifications

Recycled Resin Content, Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America