

**ADMER™ AT2614E**

PE

Mitsui Chemicals Europe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3.6</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break	<b>27</b>	MPa	ASTM D 638
Elongation at Break	<b>500</b>	%	ASTM D 638
Shore D Hardness	<b>38</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>N</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Vicat Temperature	<b>70</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Blown Film Extrusion, Film Extrusion

**Delivery form**

Pellets

**Features**

Good Adhesion

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

Europe