

ADMER™ NE062E

PE

Mitsui Chemicals Europe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	8	MPa	ASTM D 638
Tensile Strength at Break	19	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Shore D Hardness	46	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	122	°C	ASTM D 3418
Vicat Temperature	83	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Features

Good Adhesion

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

Europe