

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	63	°C	ASTM D 3418
Vicat Temperature	45	°C	ASTM D 1525
Other properties			
Density	870	kg/m ³	ASTM D 792

Characteristics

Processing

Film Extrusion

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Transparent

Features

Blending Resin, Heat Sealable, Low Odor, Copolymer

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN), Drug Master File

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa