

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	1.21	MPa	ASTM D 638
Elongation at Break	60	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	70	°C	ASTM D 3418
Glass Transition Temperature	-57	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	870	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets, White

Features

Low Odor

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

Regional Availability

North America, Europe, Asia Pacific, South and Central America