

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>1.76</b>	MPa	ASTM D 638
Elongation at Break	<b>190</b>	%	ASTM D 638
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>70</b>	°C	ASTM D 3418
Glass Transition Temperature	<b>-56.1</b>	°C	ASTM E 1356
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>874</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Delivery form

Pellets, White

#### Features

Color Stability, Good Adhesion, Low Odor, Thermal Stability

#### Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa