

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	68	°C	ASTM D 3418
Vicat Temperature	48	°C	ASTM D 1525
Optical properties			
ASTM Data			
Gloss	66	-	ASTM D 2457
Haze	4.3	%	ASTM D 1003
Other properties			
Density	875	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Features

Low Odor, Copolymer

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa