

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	76	°C	ASTM D 3418
Glass Transition Temperature	-42	°C	ASTM E 1356
Vicat Temperature	48	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	885	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

Regional Availability

North America, Europe, Asia Pacific, South and Central America