

Armobond® PE-2X

PE

R&P Polyplastic

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Yield stress	10	MPa	ISO 527
Strain at break	600	%	ISO 527

Other properties

	Value	Unit	Test Standard
Density	925	kg/m ³	ISO 1183

Processing Recommendation Extrusion

	Value	Unit	Test Standard
Type of extrusion	pipe/tube	-	-
Melt temperature	210 - 230	°C	-
Mold temperature	35	°C	-

Characteristics**Processing**

Pipe/Tube Extrusion

Regional Availability

Europe