

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|---------------|-------------------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 0.4 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |
| Thermal properties | | | |
| ASTM Data | | | |
| Melting Temperature | 120 | °C | ASTM D 3418 |
| Optical properties | | | |
| ASTM Data | | | |
| Haze | 12 | % | ASTM D 1003 |
| Other properties | | | |
| Density | 926 | kg/m ³ | ASTM D 792 |
| Film Properties | | | |
| ASTM Data | | | |
| Tensile Strength at Break, MD | 37.9 | MPa | ASTM D 882 |
| Tensile Strength at Break, TD | 34.5 | MPa | ASTM D 882 |
| Elongation at Break, MD | 700 | % | ASTM D 882 |
| Elongation at Break, TD | 800 | % | ASTM D 882 |
| Type of extrusion | blown | - | - |
| Thickness of specimen | 0.0254 | mm | - |

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Additives

Antiblocking agent

Special Characteristics

High impact or impact modified, Transparent

Features

High Gloss

Certifications

Food contact

Applications

Packaging

Regional Availability

North America