

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	961	kg/m <sup>3</sup>	ASTM D 792

Film Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break, MD	38	MPa	ASTM D 882
Tensile Strength at Break, TD	19	MPa	ASTM D 882
Elongation at Break, MD	700	%	ASTM D 882
Elongation at Break, TD	15	%	ASTM D 882
Type of extrusion	cast	-	-
Thickness of specimen	0.02	mm	-

## Characteristics

### Processing

Film Extrusion

### Delivery form

Pellets, White

### Special Characteristics

Heat stabilized or stable to heat

### Features

Blending Resin, Low Odor, Copolymer, Octene Copolymer

### Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

### Regional Availability

North America, Europe, Asia Pacific, South and Central America