

**KAPEX® D300 03**

(PC+ABS)

Ginar Technology Co.,Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>12</b>	g/10min	ASTM D 1238
Temperature	<b>260</b>	°C	-
Load	<b>5</b>	kg	-
Mold Shrinkage, MD	<b>0.007</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>44.8</b>	MPa	ASTM D 638
Elongation at Break	<b>80</b>	%	ASTM D 638
Flexural Modulus	<b>2068</b>	MPa	ASTM D 790
Flexural Strength	<b>75.8</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 105</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>507</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>93</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>1070</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Certifications**

RoHS compliant

**Applications**

Automotive, General Purpose

**Regional Availability**

Europe, Asia Pacific