

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	22	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Stress at break	15	MPa	ISO 527
Strain at break	770	%	ISO 527
Flexural modulus, 23°C	171	MPa	ISO 178
Thermal properties			
ASTM Data			
Melting Temperature	96	°C	ASTM D 3418
Vicat Temperature	81	°C	ASTM D 1525
Other properties			
Density	908	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets, White

Features

Low Odor

Certifications

Food contact, Food approval 10/2011, Food contact notification (FCN)

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America