

KUMSOLLAN® KSE6160

(PC+ABS)

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.011	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	6	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Shore A Hardness	62	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1090	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Applications

Automotive, Electrical and Electronical