

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	121	°C	ASTM D 3418
Optical properties			
ASTM Data			
Gloss	14	-	ASTM D 2457
Haze	2.4	%	ASTM D 1003
Other properties			
Density	927	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Break, MD	68.9	MPa	ASTM D 882
Tensile Strength at Break, TD	75.8	MPa	ASTM D 882
Elongation at Break, MD	580	%	ASTM D 882
Elongation at Break, TD	780	%	ASTM D 882
Type of extrusion	cast	-	-
Thickness of specimen	0.0201	mm	-

Characteristics

Processing

Film Extrusion

Features

Good Drawdown, Copolymer, Hexene Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

Europe, Near East/Africa