

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	6.89	MPa	ASTM D 638
Tensile Strength at Break	10.3	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Shore D Hardness	35	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	32	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1360	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Pellets, Black

Applications

Electrical and Electronical

Regional Availability

North America, Asia Pacific, South and Central America