

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	8.27	MPa	ASTM D 638
Tensile Strength at Break	11.7	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Shore D Hardness	42	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	30	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Pellets

Applications

Electrical and Electronical

Regional Availability

North America, Asia Pacific, South and Central America