

Product Texts

PC+ABS, ECO-conforming flame retardant with diamond sparkle appearance. Color package may affect performance.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	14	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	13.5	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	7	%	ISO 527
Flexural modulus, 23°C	2600	MPa	ISO 178
Izod notched impact strength, +23°C	14	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	3100	MPa	ASTM D 638
Tensile Strength at Yield	59	MPa	ASTM D 638
Tensile Strength at Break	46	MPa	ASTM D 638
Elongation at Yield	4	%	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	2680	MPa	ASTM D 790
Izod Impact notched, 1/8 in	213	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	95	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Yellow Card available	yes	-	-
Burning behav. 5V at thickness h	5VB	class	IEC 60695-11-20
Thickness tested	2.0	mm	-
Yellow Card available	yes	-	-
ASTM Data			
Coefficient of Thermal Expansion, MD	72	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	72	E-6/K	ASTM D 696
DTUL @ 66 psi	90	°C	ASTM D 648
DTUL @ 264 psi	82	°C	ASTM D 648
Vicat Temperature	98	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ISO 1183
Density	1190	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	245 - 275	°C	-

LEXAN™ VISUALFX™ Resin FXC630SK - Asia

(PC+ABS)

Saudi Basic Industries Corporation (SABIC)

Mold temperature	60 - 80	°C	-
Zone 1	220 - 255	°C	-
Zone 2	220 - 265	°C	-
Zone 3	245 - 275	°C	-
Nozzle temperature	245 - 275	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Certifications

Food contact

Applications

Electrical and Electronical, Packaging

Regional Availability

Asia Pacific