

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	12.8	MPa	ASTM D 638
Elongation at Break	550	%	ASTM D 638
Shore D Hardness	37	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	30	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance, Oil Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America