

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>6.89</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>12.4</b>	MPa	ASTM D 638
Elongation at Break	<b>350</b>	%	ASTM D 638
Shore D Hardness	<b>38</b>	-	ASTM D 2240

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Limiting Oxygen Index	<b>31</b>	%	ASTM D 2863

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1310</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Wire/Cable Extrusion

**Delivery form**

Pellets, Black

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Asia Pacific, South and Central America