

Lushan M-10D

PE

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	13	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	121	°C	ASTM D 3418
Vicat Temperature	70	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	921	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Special Characteristics

Transparent

Features

Good Adhesion

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

Asia Pacific