

MICROLINK XL31

PE

MICROPOL - Stamford Products Limited

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|---------------|-------------|----------------------|
| ISO Data | | | |
| Stress at break | 23 | MPa | ISO 527 |
| Strain at break | >50 | % | ISO 527 |
| Flexural modulus | 750 | MPa | ISO 178 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 940 | kg/m ³ | ISO 1183 |

Characteristics**Processing**

Rotational Molding

Delivery form

Powder

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Crosslinkable, Good Adhesion, Thermal Stability

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance

Regional Availability

Europe