

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6.6	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	64	MPa	ISO 527
Tensile Strength	22	MPa	ISO 527
Strain at break	943	%	ISO 527
Flexural modulus, 23°C	77	MPa	ISO 178
Shore A hardness	90	-	ISO 7619-1
Shore D hardness	34	-	ISO 7619-1
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	96	°C	ISO 11357-1/-3
Vicat softening temperature, A	73	°C	ISO 306
Other properties			
Density	902	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion

Special Characteristics

High impact or impact modified, Transparent

Features

Barrier Properties, Blending Resin, Heat Sealable

Regional Availability

Europe