

Revolve® M-638

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	15.5	MPa	ISO 527
Flexural modulus, 23°C	625	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	44	°C	ISO 75-1/-2
Other properties			
Density	935	kg/m ³	ISO 1183

Characteristics**Processing**

Rotational Molding

Delivery form

Powder, Black

Special Characteristics

High impact or impact modified

Applications

General Purpose

Regional Availability

Europe, Asia Pacific