

Revolve® M-716 Conductive

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	16.8	MPa	ISO 527
Flexural modulus, 23°C	645	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	47	°C	ISO 75-1/-2
Other properties			
Density	935	kg/m ³	ISO 1183

Characteristics

Processing

Rotational Molding

Delivery form

Powder, Black

Special Characteristics

Increased electrical conductivity, High impact or impact modified

Applications

General Purpose

Regional Availability

Europe, Asia Pacific